

AMENDMENT TO THE SPECIFICATION

Please amend the specification beginning on page 24, line 23 as follows:

(l) Chromium plating on the surface of copper powder was conducted by electric plating using a rotating horizontal barrel apparatus. Average plating layer thickness was 10 nm. A cross-sectional view of the metal powder after plating 7 is shown in Fig. 7.